

				Report Date:	4/3/2015			
Ambient Bamboo Floors				Project #:	0721473	1473		
				Report Of:	ASTM D 6007			
8125 Stayton Dr Unit C					0721473-9			
Jessup, MD 20794				Sample #:	7713			
USA			Dementing	Benchmark Holdings, LLC				
				Reporting	2710 West 5th Avenue, Eugene, OR 97402 USA			
ASTM D 6007			Lap:	Phone:541/484-9212 - Fax: 541/344-2735		35		
AS	STM D6007	Determinin	g Form			g Small Chamber		
Chamber Results				Production Data				
		Impinger				ral Horizontal		
		#1		Mill Code:		Prod Date:	17-May-13	
Observed Flow Rate (I/m):		1.000		Prod Group:		Control Date:	NS	
Corr. Vol. of Air Sample:		30.724		Test Date:	2-Apr-15	Coll. Date:	4-Mar-15	
Raw Absorbance Values:		0.003						
		0.008				CHAMBER ID#:	2	
		0.005				Chamber Conditions		
Average Absorbance:		0.005				Barometric Pressure (in):	30.70	
Unadjusted PPM:		0.011				Dry Bulb Temp (°F):	78.00	
Temp. Correction Factor 77°F:		0.94				Relative Humidity (%):	47.40	
R.H. Correction Factor 50% RH:		1.05				Length of Test (minutes):	30.00	
Standardized Concentration PPM:		0.011						
	Maxim	um PPM: *						
	* Sample is solid bamboo, tested as if it were HWPW. Product is not regulated, however,							
Comments: emissions as tested were below published CARB Phase 2 standard for HWPW (0.05 ppm).								
Parameters:								
Loading Ratio: 0.430					Volume =	.1191863m³		
Chamber Dimensions:	.49213m x .49213m x .49213m			<u></u> ו				
Air Exchange Rate:	0.50 ± 0.05 air changes per hour							

*The chamber is activated under positive pressure. The air sampling rate was 1.0 liters per minute at 30 ±2 minutes.

*The samples were conditioned for seven days prior to testing at 70° to 80° F and 45% to 55% relative humidity. During conditioning, the formaldehyde background level was 0.01 parts per million or less.

*Services performed for this project have been conducted with a level of care and skill ordinarily exercised by members of the profession currently practicing in this area under similar conditions and restraints. No warranty, expressed or implied, is made.

*This report has been produced for the exclusive use of: <u>Ambient Bamboo Floors</u> (client), and may not be reproduced except in its entirety, and only with the expressed, written approval of BMI. No one other than BMI's client shall be entitled to rely upon this report or the information contained herein. Any such unauthorized reliance on or use of this report will be at the third party's sole risk.



Respectfully Submitted,

Benchmark Holdings LLC

Travis R. Snapp Managing Director / COO Benchmark International LLC