

			Report Date:	4/11/2016			
Ambient Bamboo Floors			Project #:	0721473	73		
			Report Of:	ASTM D 60	07		
8125 Stayton Dr Unit C				0721473-20			
Jessup, MD 20794			Sample #:	2016-0982			
USA			Peperting	Benchmark Holdings, LLC			
			Lab:	Benchmark Holdings, LLC 2710 West 5th Avenue, Eugene, OR 97402 USA			
ASTM D 6007			LaD.	Phone:541/484-9212 - Fax: 541/344-2735			
ASTM D6007 Determining Formaldehyde Emissions Using Small Chamber							
Chamber Results			Production Data				
	Impinger		Product:	Strand Eucalyptus Flooring 14mm			
	#1		Mill Code:	NS	Prod Date:	NS	
Observed Flow Rate (I/m):	1.000		Prod Group:		Control Date:	NS	
Corr. Vol. of Air Sample:	29.612		Test Date:	7-Apr-16	Coll. Date:	22-Mar-16	
Raw Absorbance Values:	0.006						
	0.005				CHAMBER ID#:	3	
0.009					Chamber Conditions		
Average Absorbance: 0.0					Barometric Pressure (in):	29.60	
Unadjusted PPM:	0.019				Dry Bulb Temp (°F):	78.20	
Temp. Correction Factor 77°F:	0.93				Relative Humidity (%):	50.30	
R.H. Correction Factor 50% RH:	0.99				Length of Test (minutes):	30.00	
Standardized Concentration PPM:	0.018						
Comments: *Sample is solid eucalyptus flooring, tested as if it were HWPW.							
Parameters:							
Loading Ratio: 0.430				Volume =	.1191863m³		
Chamber Dimensions: .49213m x .49213m x .49213m							
Air Exchange Rate: 0.50 ± 0.05 air changes per hour							

*The chamber is activated under positive pressure. The air sampling rate was 1.0 liters per minute at 30 ±2 minutes.

*The samples were conditioned for seven days prior to testing at 70° to 80° F and 45% to 55% relative humidity. During conditioning, the formaldehyde background level was 0.01 parts per million or less.

*Services performed for this project have been conducted with a level of care and skill ordinarily exercised by members of the profession currently practicing in this area under similar conditions and restraints. No warranty, expressed or implied, is made.

*This report has been produced for the exclusive use of: Ambient Bamboo Floors (client),

and may not be reproduced except in its entirety, and only with the expressed, written approval of BMI. No one other than BMI's client shall be entitled to rely upon this report or the information contained herein. Any such unauthorized reliance on or use of this report will be at the third party's sole risk.



Respectfully Submitted,

Benchmark Holdings LLC

Travis R. Snapp Managing Director / COO Benchmark International LLC