



BMIH
Benchmark International

LAB REPORT

Submitted to:

 **ambient** BAMBOO FLOORS

April 14th, 2016





Ambient Bamboo Floors
8125 Stayton Dr. Unit C
Jessup, MD 20794
(301) 498-0234

Two (2) samples of flooring was submitted to this laboratory for Janka ball hardness testing by Ambient Bamboo. Test, associated standard, and results are listed in the table below.

Janka Ball Hardness - ASTM D1037			
Sample ID	Test 1 (lbf) Face	Test 2 (lbf) Face	Average (lbf)
Strand Bamboo Solid 9/16"	5,342	4,328	4,835
Strand Eucalyptus Solid 9/16"	4,879	5,300	5,090

This report has been produced for the exclusive use of Ambient Bamboo, and may not be reproduced except in its entirety, and only with the expressed, written approval of Benchmark International (BMI). No one other than BMI's client shall be entitled to rely upon this report or the information contained herein; any such unauthorized reliance on or use of this report will be at the third party's sole risk.

Services performed for this project have been conducted with a level of care and skill ordinarily exercised by members of the profession currently practicing in this area under similar conditions and restraints. No warranty, expressed or implied, is made.

Respectfully Submitted,
Benchmark International

Travis R. Snapp
President & Founder