Benchmark

Reporting Laboratory:

Benchmark International, LLC (BMI) 2710 West 5th Avenue

Eugene, Oregon, USA 97402

Phone: +1 (541) 484-9212 / FAX: +1 (541) 344-2735

TESTING CONDUCTED ON BEHALF OF THE NAMED CLIENT BELOW:

Ambient Bamboo Floors 8230 Preston Ct. Unit C Jessup, MD 20794 USA

REPORT INFORMATION:

Report Date: November 17, 2020

BMI Client/Project Number: 0721473

Report of: Finished Goods Ind #1 (Face Exposed)

BMI Lab Report Number: 0721473-41

Sample ID Number(s): 2020-1233

ASTM D6007-14 Standard Test Method for Determining Formaldehyde Concentration in Air from Wood Products Using a Small Scale Chamber
ASTM D5197-16: Standard Test Method for Determination of Formaldehyde and Other Carbonyl Compounds in Air (Active Sampler Methodology)

Back-to-Back Sample Configuration (Face Exposed)

CHAMBER TEST CONDITIONS/PARAMETERS							
Product Type:	Finished Goods						
Chamber Load Ratio (m ² /m ³):	0.86						
Chamber Dimensions (m):	0.39 x 0.39 x 0.39 (Nominal)						
Chamber Volume (m ³):	0.06m ³						
Air Exchange Rate:	1.0 +/- 0.05 air changes per hour						
Chamber Q/A Ratio (+/- 2%):	1.173						
No. Specimens in Charge:	1						
No. Faces Exposed:	2						
Temperature (°C):	Avg:	25.2	Min:	25.0	Max:	25.4	
Relative Humidity (%):	Avg:	49	Min:	49	Max:	50	
Length of Test (minutes):	60						

TEST RESULTS					
	Value:				
Observed Air Flow Rate (Liters/min):	1.00				
Corrected Volume of Air Sample (Liters):	60.0				
Sample Concentration (µg/mL):	0.004				
Sample Eluent Dilution Factor:	N/A				
Unadjusted Concentration in Air (ppm):	0.001				
Temperature Correction Factor to 25 :	0.98				
Relative Humidity Correction Factor to 50% R.H.:	1.02				
Standardized Concentration in Air (ppm):	**<0.005				
**<0.005ppm = Test result is below the limit of quantification					

This report has been produced for the exclusive use of:

Ambient Bamboo Floors

and may not be reproduced except in its entirety, and only with the express written permission of
Benchmark International, LLC (BMI). No one other than the named BMI Client identified in this test
report shall be entitled to rely upon this report or the information contained or referenced herein. Any
such unauthorized reliance upon or use of this test report will be at the third party's sole risk.

NOTE 1: Unless otherwise agreed in writing in advance by a duly authorized member of BMI
management, test services are subject to the current Benchmark Holdings, LLC Terms and Conditions of
Service in effect at the time the test sample is submitted to the BMI laboratory. All test reports are
subject to the current Benchmark Holdings, LLC Inspection and Test Report Publication Guidelines.
Report users are responsible for contacting BMI to obtain a copy of the current inspection and test
report publication guidelines and/or to obtain written authorization to publish or reproduce this test
report.

NOTE 2: Test results are for information purposes only and do not constitute an independent product certification unless otherwise specified in valid BMH certification documents. Unless otherwise noted in this test report, test results apply only to the test samples as-received from the Client or other person(s) responsible for the sampling stage. Test results, to include professional opinions, interpretations, or judgments made if any, apply only to the specific product(s) and the lot(s)/batch(es) evaluated and identified in this test report. Report users must not represent test results in a manner so as to state or imply the test results may be applied to other product(s) or lot(s)/batch(es) that were not specifically included in the test evaluation.

NOTE 3: Services performed for this project have been conducted with a level of care and skill ordinarily exercised by members of the profession currently practicing in this area under similar conditions and constraints. No warrantv. expressed or implied. is made.

CUSTOMER-SUPPLIED PRODUCT AND SAMPLE DATA						
Product Name/Description:	14mm Engineered Strand Woven Bamboo Flooring					
Panel Manufacturer:	Not Specified	Production Date:	9/15/2020			
Supplier: (if different than panel mfr)		Sample Collection Date:	11/5/2020			
Nominal Product Thickness:		Specimen Test Date:	11/16/2020			
Nominal Product Dimensions (L x W):		Sample Wrapping Method:	Wrapped Together in Vapor Retarder			
Face Surface Condition:	Stained/Coated	Back Surface Condition:	Stained/Coated			
Lot/Batch No.:	N/S	Panel Production Line:				
Resin Supplier Name:	Not Specified	Resin Name/Type:	Not Specified			
Sample Collected by:	Client	Sample Collector Name:	Jon Livingston			

TEST ANNOTATIONS

- 1) The test chamber is activated under positive pressure. The air sampling rate was 1.0 liters per minute (L/min) for 60 +/- 2 minutes.
- 2) Unless otherwise noted, test specimens were prepared per test method requirements. Specimens were conditioned for seven (7) days prior to testing. The specimen conditioning environment was maintained at 75 +/- 5°F (24 +/- 3°C) and 50% +/- 5%
- 3) During conditioning and test, the background concentration of formaldehyde in air was

0.005 ppm or less

OTHER COMMENTS

Not Applicable

Respectfully Submitted,

Laboratory Manager

Benchmark Holdings, LLC (BMH)

