TEST REPORT

SCOPE OF WORK
MAGNESIUM OXIDE BOARD

REPORT NUMBER
240125004SHF-012-R1

TEST DATE(S)
2024-01-25 - 2024-03-21

ORIGINAL ISSUE DATE	[REVISED DATE]
2024-03-21	2024-04-15

PAGES
5

DOCUMENT CONTROL NUMBER
LFT-APAC-SHF-OP-10l(February 1, 2024)
© 2024 INTERTEK



Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch

Test Report

Statement

1.This report is invalid without company's special seal for testing on the assigned page.

2.This report is invalid without an authorized person's signature.

3.This report is invalid if altered.

4.Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Don't copy this report in partial without any official approval in written by our company. This report is invalid without re-stamping the special seal for testing in copying report.

5.This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample(s) tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

6.Except for the obligation, responsibility and liability (if any) for the appropriateness and professionality of afore-mentioned testing itself within the scope and amount of the testing fee received, Intertek does not and will not accept any other obligation or liability.

7.If the Client has any questions about the test results, Intertek B&C should be informed within the storage period of the samples. The sample storage period ends 5 working days after the offical report issue date. Samples of certification program are retained for the period required by the certification rules. The samples storage period shall be calculated according to the issue date of the original report in the case of quoting results and modifying reports.

8.Intertek B&C will service this report for the entire test record retention period. The test record retention period ends 6 years after this report original issue date. The test record retention period for certification program is 10 years. Test records and other pertinent project documentation will be retained for the entire test record retention period.

9.The report was digital signed by Shang Hai, Intertek Group plc, please using Adobe Acrobat Reader to verify the authenticity.

Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch
Plant 5, No. 6958 Daye Road, Fengxian District, Shanghai, China
Tel: +86 21-61136116 Fax: 021-61189921
Website: www.intertek.com

Test Report

Original Issue Date: 2024-03-21 Revised Date: 2024-04-15 Intertek Report No. 240125004SHF-012-R1

Applicant: Ambient Building Products

Address: 8230 Preston Ct Ste C, Jessup, MD 20794

Manufacturer: Ambient Building Products

Address: 8230 Preston Ct Ste C, Jessup, MD 20794

Test Type: Performance test, samples provided by the applicant.

Product Information

Product Name	Model	Specification
MAGNESIUM OXIDE BOARD	/	1220mm*2440mm*12mm
Sample ID	**Sample Amount**	**Sample Received Date**
S240125004SHF.006	1 package	2024-01-23
Sample Description		
1220mm*2440mm*12mm		

Test Methods And Standards

Test Standard	EN 12467:2012+A2:2018 5.4.6
Specification Standard	/
Test Conclusion	The samples were tested according to the above standards, and the results are shown in the following page.

Note:

1.This report does not involve sampling. The report only reflects conformity of the tested items of the samples provided by the testing applicant. Representativeness and authenticity of the submitted samples are responsibilities of the testing applicant.

Report Authorized

Flora Fan

Name: Flora Fan

Title: Reviewer

Jackie Zhou

Name: Jackie Zhou

Title: Project Engineer

intertek
Total Quality. Assured.

Test Report

Original Issue Date: 2024-03-21 Revised Date: 2024-04-15 Intertek Report No. 240125004SHF-012-R1

Test Items, Method and Results:

EN 12467:2012+A2:2018 Fibre-cement flat sheets - Product specification and test methods		
Clause	Requirement - Test	Result - Remark
5.4	Physical requirements and characteristics	
5.4.6	Water vapour permeability for Category D For flat sheets used as rigid underlays, the water vapour resistance value μ shall be determined according to 7.3.4 and shall be specified in the manufacturer's literature. The μ value obtained from the test shall not be higher than the value specified by the manufacturer.	Specified value, μ: 12.8 Water vapor resistance factor, μ: 12.4

Test Report

Original Issue Date: 2024-03-21 Revised Date: 2024-04-15 Intertek Report No. 240125004SHF-012-R1

Appendix A: Sample Received Photo

Revision:

NO.	Date	Changes
240125004SHF-012	2024-03-21	First issue
240125004SHF-012-R1	2024-04-15	Revised the product name as per applicant's requirement.

Note: Since the issue date of 240125004SHF-012-R1 report, the original report 240125004SHF-012 was cancelled at the same time.